

# TECHNICAL DATA SHEET

Organic pigment for coatings&inks



Edition 01.01.2011

## Pigment Yellow 17 UN8217

### Identification


Chem Group:	Disazo
C.I.No.:	21105
CAS No.:	4531-49-1
ECNO.:	224-867-1
Counter Type:	Diarylide Yellow AAOA

### Product Description

Pigment Yellow 17 UN8217 is a greenish yellow pigment with good transparent and bright luster



Full shade



Reduction 1:10

### Application

Recommended for	Offset inks, water-based inks, textile printing
Suggested for	Solvent-based inks

### Physical Data

Appearance	Yellow Powder	Oil absorption(ml/100g)	35-50
Density(g/cm <sup>3</sup> )	1.6	Water soluble matter(%)	≤ 1.5
Moisture(%)	≤ 2.0	Electric Conductivity(us/cm)	≤ 600
pH-value	6.0-7.0		

### Fastness Data

Water	5	Butyl Acetate	4-5
Acid	5	Benzene	4-5
Alkali	5	Ketone	4-5
Oil	4	Ethyl Alcohol	4-5
Heat Stability(°C)	180	Light Fastness	5

### Note:

The above information is provided as guidelines only. It is important that the customers evaluate any product in their own resin system to determine suitability.

### HUPC CHEMICAL CO.LTD

Room 301, Building B2, No.206 ZhenHua Road, HangZhou, China  
Tel:0086-571-89905373 Email: info@unionpigment.com

Web Site: www.union-pigment.com