

# TECHNICAL DATA SHEET

Organic pigment for coatings&inks



Edition 01.01.2011

## Pigment Red 170 UN8161

### Identification

Chem Group:	Mono azo
C.I. No.:	12475
CAS No.:	2786-76-7
EC NO.:	220-509-3
Counter Type:	Naphthol Red F2RK

### Product Description



Full shade



Reduction 1:10

### Application

Recommended for	paint and plastic
Suggested for	

### Physical Data

Appearance	Red Powder		
Density(g/cm <sup>3</sup> )	1.5	Oil absorption(ml/100g)	30-50
Moisture(%)	≤1.5	Water soluble matter(%)	≤1.5
pH-value	6.0-7.5	Electric Conductivity(us/cm)	≤600

### Fastness Data

Water	5	Butyl Acetate	5
Acid	5	Benzene	4~5
Alkali	5	Ketone	4~5
Oil	4~5	Ethyle Alcohol	4~5
Heat Stability(°C)	180	Light Fastness	7

### Note:

The above information is provided as guidelines only. It is important that the customers evaluate any product in their own resin system to determine suitability.

### HUPC CHEMICAL CO.LTD

Room 301,Building B2,No.206 ZhenHua Road, HangZhou, China  
Tel:0086-571-89905373

Email: info@unionpigment.com

Web Site: www.union-pigment.com