

TECHNICAL DATA SHEET

Organic pigment for coatings&inks



Edition 01.01.2011

Pigment Red 48:1 UN8118

Identification

Chem Group:	Mono Azo
C.I. No.:	15865:1
CAS No.:	7585-41-3
EC NO.:	231-494-8
Counter Type:	Barium Red 2B

Product Description

Pigment Red 48:1 UN8118 is red powder pigment with easily dispersible, strong strength



Full shade



Reduction 1:10

Application

Recommended for	Aqueous inks, Aqueous coating
Suggested for	/

Physical Data

Appearance	Red Powder		
Density(g/cm ³)	1.8	Oil absorption(ml/100g)	30-55
Moisture(%)	≤4.0	Water soluble matter(%)	≤2.5
pH-value	7.0-8.0	Electric Conductivity(us/cm)	≤600

Fastness Data

Water	4	Butyl Acetate	4
Acid	4	Benzene	4
Alkali	4	Ketone	4
Oil	4	Ethyle Alcohol	5
Heat Stability(°C)	180	Light Fastness	6

Note:

The above information is provided as guidelines only. It is important that the customers evaluate any product in their own resin system to determine suitability.

HUPC CHEMICAL CO.LTD

Room 301, Building B2, No.206 ZhenHua Road, HangZhou, China
Tel: 0086-571-89905373 Email: info@unionpigment.com

Web Site: www.union-pigment.com