

# TECHNICAL DATA SHEET

Organic pigment for coatings&inks



Edition 01.01.2011

## Pigment Red 63:1 UN8147

### Identification

Chem Group:	Mono Azo
C.I. No.:	15880:1
CAS No.:	6417-83-0
EC NO.:	229-142-3
Counter Type:	Lake Bordeaux 10B

### Product Description

Pigment Red 63:1 UN8147 is purplish red pigment that with good solvent resistance and good migration resista



Full shade



Reduction 1:10

### Application

Recommended for	industrial paint.
Suggested for	/

### Physical Data

Appearance	Red Powder		
Density(g/cm <sup>3</sup> )	1.8	Oil absorption(ml/100g)	35-55
Moisture(%)	≤3.5	Water soluble matter(%)	≤2.5
pH-value	7.0-8.0	Electric Conductivity(us/cm)	≤600

### Fastness Data

Water	4	Butyl Acetate	3~4
Acid	4	Benzene	4
Alkali	4	Ketone	4
Oil	4	Ethyle Alcohol	4
Heat Stability(℃)	160	Light Fastness	5~6

### Note:

The above information is provided as guidelines only. It is important that the customers evaluate any product in their own resin system to determine suitability.

### HUPC CHEMICAL CO.LTD

Room 301,Building B2,No.206 ZhenHua Road, HangZhou, China  
Tel:0086-571-89905373 Email: info@unionpigment.com

Web Site: www.union-pigment.com

.nce.