TECHNICAL DATA SHEET

Organic pigment for coatings&inks



Edition 01.01.2014

Pigment Violet 23 UN8815

Identification

 Chem Group:
 Dioxaxine

 C.I. No.:
 51319

 CAS No.:
 6358-30-1

 ECNO.:
 228-767-9

Counter Type: Carbazol Violet, Dioxazine Violet

Product Description

Pigment Violet 23 UN8815 is general application in reddish shade.



Full shade Reduction 1:10

Application

Recommended for inks, textile printing, plastic, paints.

Suggested for /

Physical Data

| Appearance | V10. | let | P | 'owde | r |
|------------|------|-----|---|-------|---|
|------------|------|-----|---|-------|---|

| Density(g/cm³) | 1.5 | Oil absorption(ml/100g) | 30-60 |
|----------------|---------|------------------------------|-------|
| Moisture(%) | ≤2.0 | Water soluble matter(%) | ≤1.5 |
| pH-value | 5.0-7.0 | Electric Conductivity(us/cm) | ≤600 |

Fastness Data

| Water | 5 | Butyl Acetate | 5 |
|-------------------|-----|----------------------|-----|
| Acid | 5 | Benzene | 5 |
| Alkali | 5 | Ketone | 5 |
| Oil | 5 | Ethyle Alcohol | 5 |
| Heat Stability(℃) | 200 | Light Fastness | 7~8 |

Note:

The above information is provided as guidelines only. It is important that the customers evaluate any product in their own resin system to determine suitability.

HUPC CHEMICAL CO.LTD

Room 301,Building B2,No.206 ZhenHua Road,HangZhou,China Tel:0086-571-89905373 Email: info@unionpigment.com

Web Site: www.union-pigment.com