

# TECHNICAL DATA SHEET

Organic pigment for coatings&inks



Edition 01.01.2014

## Pigment Violet 23 UN8822

### Identification

Chem Group:	Dioxaxine
C.I.No.:	51319
CAS No.:	6358-30-1
ECNO.:	228-767-9
Counter Type:	Carbazol Violet,Dioxazine Violet

### Product Description

Pigment Violet 23 UN8822 is solvent based system,bluish with high performance.



Full shade



Reduction 1:10

### Application

Recommended for	Solvent based inks, NC ink, solvent based paint
Suggested for	UV ink

### Physical Data

Appearance	Violet Powder		
Density(g/cm <sup>3</sup> )	1.5	Oil absorption(ml/100g)	30-60
Moisture(%)	≤2.0	Water soluble matter(%)	≤1.5
pH-value	5.0-7.0	Electric Conductivity(us/cm)	≤600

### Fastness Data

Water	5	Butyl Acetate	5
Acid	5	Benzene	5
Alkali	5	Ketone	5
Oil	5	Ethyle Alcohol	5
Heat Stability(°C)	200	Light Fastness	7~8

### Note:

The above information is provided as guidelines only. It is important that the customers evaluate any product in their own resin system to determine suitability.

### HUPC CHEMICAL CO.LTD

Room 301,Building B2,No.206 ZhenHua Road, HangZhou, China

Tel:0086-571-89905373

Email: info@unionpigment.com

Web Site: www.union-pigment.com