

TECHNICAL DATA SHEET

Organic pigment for coatings&inks



Edition 01.01.2011

Pigment Yellow 12 UN8208

Identification

Chem Group:	Disazo
C.I. No.:	21090
CAS No.:	6358-85-6
EC NO.:	228-787-8
Counter Type:	Diarylide Yellow AAA

Product Description

Pigment Yellow 12 UN8208 is economic type



Full shade



Reduction 1:10

Application

Recommended for	Offset inks
Suggested for	

Physical Data

Appearance	Yellow Powder	Oil absorption(ml/100g)	40-50
Density(g/cm ³)	1.5	Water soluble matter(%)	≤ 1.5
Moisture(%)	≤ 2.0	Electric Conductivity(us/cm)	≤ 600
pH-value	6.0-7.0		

Fastness Data

Water	4	Butyl Acetate	4
Acid	5	Benzene	4
Alkali	5	Ketone	4
Oil	4	Ethyl Alcohol	4
Heat Stability(°C)	180	Light Fastness	5

Note:

The above information is provided as guidelines only. It is important that the customers evaluate any product in their own resin system to determine suitability.

HUPC CHEMICAL CO.LTD

Room 301,Building B2,No.206 ZhenHua Road, HangZhou, China
Tel:0086-571-89905373 Email: info@unionpigment.com

Web Site: www.union-pigment.com