

TECHNICAL DATA SHEET

Organic pigment for coatings&inks



Edition 01.01.2014

Pigment Yellow 14 UN8213

Identification

Chem Group:	Disazo
C.I. No.:	21095
CAS No.:	5468-75-7
EC NO.:	226-789-3
Counter Type:	Diarylide Yellow AAOT

Product Description

Pigment Yellow 14 UN8213 is high transparent, low viscosity, and good steaming resistance



Full shade



Reduction 1:10

Application

Recommended for	Solvent based inks, PU ink
Suggested for	

Physical Data

Appearance	Yellow Powder	Oil absorption(ml/100g)	35-45
Density(g/cm ³)	1.6	Water soluble matter(%)	≤1.5
Moisture(%)	≤2.0	Electric Conductivity(us/cm)	≤600
pH-value	6.0-7.0		

Fastness Data

Water	5	Butyl Acetate	4
Acid	5	Benzene	4
Alkali	5	Ketone	4
Oil	4	Ethyl Alcohol	5
Heat Stability(°C)	180	Light Fastness	5

Note:

The above information is provided as guidelines only. It is important that the customers evaluate any product in their own resin system to determine suitability.

HUPC CHEMICAL CO.LTD

Room 301,Building B2,No.206 ZhenHua Road, HangZhou, China

Tel:0086-571-89905373

Email: info@unionpigment.com

Web Site: www.union-pigment.com