

TECHNICAL DATA SHEET

Organic pigment for coatings&inks



Edition 01.01.2011

Pigment Yellow 55 UN8219

Identification

Chem Group:	Disazo
C.I. No.:	21096
CAS No.:	6358-37-8
EC NO.:	228-771-0
Counter Type:	Diarylide Yellow AAPT

Product Description

Pigment Yellow 55 UN8219 is a general type yellow with strong reddish shade



Full shade



Reduction 1:10

Application

Recommended for	Industrial paints, water-based paints, textile printing
Suggested for	Offset inks

Physical Data

Appearance	Yellow Powder	Oil absorption(ml/100g)	35-55
Density(g/cm ³)	1.5	Water soluble matter(%)	≤1.5
Moisture(%)	≤2.0	Electric Conductivity(us/cm)	≤600
pH-value	6.0-7.5		

Fastness Data

Water	5	Butyl Acetate	4
Acid	5	Benzene	4
Alkali	5	Ketone	4
Oil	4	Ethyl Alcohol	4-5
Heat Stability(°C)	150	Light Fastness	6-7

Note:

The above information is provided as guidelines only. It is important that the customers evaluate any product in their own resin system to determine suitability.

HUPC CHEMICAL CO.LTD

Room 301,Building B2,No.206 ZhenHua Road, HangZhou, China

Tel:0086-571-89905373

Email: info@unionpigment.com

Web Site: www.union-pigment.com