

# TECHNICAL DATA SHEET

Organic pigment for coatings&inks



Edition 01.01.2011

## Pigment Yellow 65 UN8221

### Identification

Chem Group:	Mono Azo
C.I.No.:	11740
CAS No.:	6528-34-3
ECNO.:	229-419-9
Counter Type:	Hansa Yellow RN

### Product Description

Pigment Yellow 65 UN8221 is reddish yellow shade and with good hiding power



Full shade



Reduction 1:10

### Application

Recommended for	Road marking paints, industrial paints, water-base decorative paints,
Suggested for	Solvent-based decorative paints

### Physical Data

Appearance	Yellow Powder	Oil absorption(ml/100g)	30-50
Density(g/cm <sup>3</sup> )	1.6	Water soluble matter(%)	≤ 1.5
Moisture(%)	≤ 2.0	Electric Conductivity(us/cm)	≤ 600
pH-value	6.0-7.0		

### Fastness Data

Water	5	Butyl Acetate	4
Acid	5	Benzene	4
Alkali	5	Ketone	4
Oil	4	Ethyl Alcohol	4
Heat Stability(°C)	150	Light Fastness	6

### Note:

The above information is provided as guidelines only. It is important that the customers evaluate any product in their own resin system to determine suitability.

### HUPC CHEMICAL CO.LTD

Room 301,Building B2,No.206 ZhenHua Road, HangZhou, China

Tel:0086-571-89905373

Email: info@unionpigment.com

Web Site: www.union-pigment.com