

# TECHNICAL DATA SHEET

Organic pigment for coatings&inks



Edition 01.01.2011

## Pigment Yellow 74 UN8222

### Identification

Chem Group:	Mono Azo
C.I.No.:	11741
CAS No.:	6358-31-2
ECNO.:	228-768-4
Counter Type:	Hansa Yellow 5GX

### Product Description

Pigment Yellow 74 UN8222 is a greenish shade yellow pigment, transparent and have good dispersibility.



Full shade



Reduction 1:10

### Application

Recommended for	Water-based inks, water-based decorative paints, textile printing
Suggested for	Offset inks, solvent-based inks, industrial paints

### Physical Data

Appearance	Yellow Powder	Oil absorption(ml/100g)	30-50
Density(g/cm <sup>3</sup> )	1.5	Water soluble matter(%)	≤ 1.5
Moisture(%)	≤ 2.0	Electric Conductivity(us/cm)	≤ 600
pH-value	6.0-7.5		

### Fastness Data

Water	4-5	Butyl Acetate	4
Acid	5	Benzene	4
Alkali	5	Ketone	4
Oil	4	Ethyl Alcohol	5
Heat Stability(°C)	140	Light Fastness	6-7

### Note:

The above information is provided as guidelines only. It is important that the customers evaluate any product in their own resin system to determine suitability.

### HUPC CHEMICAL CO.LTD

Room 301, Building B2, No.206 ZhenHua Road, HangZhou, China  
Tel:0086-571-89905373 Email: info@unionpigment.com

Web Site: www.union-pigment.com