

# TECHNICAL DATA SHEET

Organic pigment for coatings&inks



Edition 01.01.2011

## Pigment Yellow 83 UN8228

### Identification

Chem Group:	Disazo
C.I. No.:	21108
CAS No.:	5567-15-7
EC NO.:	226-939-8
Counter Type:	Diarylide Yellow HR

### Product Description

Pigment Yellow 83 UN8228 is a reddish shade and opaque



Full shade



Reduction 1:10

### Application

Recommended for	Textile printing, industrial paints, water-based paints, solvent-based paints
Suggested for	

### Physical Data

Appearance	Yellow Powder	Oil absorption(ml/100g)	30-55
Density(g/cm <sup>3</sup> )	1.6	Water soluble matter(%)	≤ 1.5
Moisture(%)	≤ 2.0	Electric Conductivity(us/cm)	≤ 600
pH-value	6.0-7.5		

### Fastness Data

Water	5	Butyl Acetate	5
Acid	5	Benzene	5
Alkali	5	Ketone	5
Oil	5	Ethyl Alcohol	5
Heat Stability(°C)	200	Light Fastness	7

### Note:

The above information is provided as guidelines only. It is important that the customers evaluate any product in their own resin system to determine suitability.

### HUPC CHEMICAL CO.LTD

Room 301,Building B2,No.206 ZhenHua Road, HangZhou, China  
Tel:0086-571-89905373 Email: info@unionpigment.com

Web Site: www.union-pigment.com